

REMARKS


Entry of the amendments to the specification and claims before examination of the application is respectfully requested. These claims have been amended to remove multiple dependencies and patentably define over the art of record.

If there are any questions regarding this Preliminary Amendment or this application in general, a telephone call to the undersigned would be appreciated since this should expedite the prosecution of the application for all concerned.

If necessary to effect a timely response, this paper should be considered as a petition for an Extension of Time sufficient to effect a timely response, and please charge any deficiency in fees or credit any overpayments to Deposit Account No. 05-1323 (Docket #095309.56876US).

October 5, 2005

Respectfully submitted,



Song Zhu
Registration No. 44,420
Donald D. Evenson
Registration No. 26,160

CROWELL & MORING LLP
Intellectual Property Group
P.O. Box 14300
Washington, DC 20044-4300
Telephone No.: (202) 624-2500
Facsimile No.: (202) 628-8844
DDE:SZ:aw

398640v1

Exhaust gas aftertreatment device and method

EXHAUST GAS AFTERTREATMENT DEVICE AND METHOD

5 BACKGROUND AND SUMMARY OF THE INVENTION

The invention relates to an apparatus and a method for exhaust gas aftertreatment for mobile applications ~~as described in the preamble of claim 1 and claim 11, respectively.~~

It is essential to comply with appropriate statutory emission
10 regulations if motor vehicles with spark-ignition and in particular diesel engines are to be used. In this context, catalytic reduction of NO_x using hydrogen is regarded as advantageous. This catalytic removal of nitrogen oxides from the combustion exhaust gases of motor vehicles is carried out using hydrogen at suitable catalytic converters in
15 accordance with the reaction $2\text{NO} + 2\text{H}_2 \rightarrow \text{N}_2 + 2\text{H}_2\text{O}$.

In some of the known methods for removing nitrogen oxides by NO_x reduction, the hydrogen required for the reaction is carried along in the vehicle, e.g., in pressurized tanks, liquid hydrogen tanks or metal hydride stores. One drawback of this process is that large, heavy tanks
20 are required to carry the hydrogen, and moreover these tanks only have a very limited capacity, which requires short top-up intervals.

EP 537 968 A1 has disclosed an apparatus for the catalytic reduction of nitrogen oxides in exhaust gases from motor vehicles with hydrogen being supplied. The hydrogen is generated onboard the motor vehicle by partial oxidation or reforming of methanol at a suitable catalytic
5 converter. The catalytic converters are heated by virtue of being arranged in the hot exhaust-gas stream from the engine.

DE 101 20 097 A1 has disclosed an exhaust gas purification system in a vehicle with a reforming reactor for extracting hydrogen from fuel, in which system the hydrogen can be fed to an exhaust gas stream in an
10 exhaust pipe an internal combustion engine upstream of an exhaust gas catalytic converter. The reforming reactor has a feed device for oxygen and/or water and is connected to a secondary branch of the exhaust pipe, it being possible for oxygen and water for reforming to be supplied in the form of an exhaust gas part-stream via the secondary branch.

15 To enable the arrangement of the respective components for exhaust gas purification in the abovementioned patent documents to be implemented, it is necessary to provide a correspondingly large installation space for the exhaust gas aftertreatment apparatus, which is consequently relatively unwieldy.

20 Therefore, it is an object of the invention to provide a method and an apparatus for exhaust gas aftertreatment which can be used to optimize the installation space so as to effect a more compact design.

The invention solves this problem by providing an exhaust gas aftertreatment device ~~having the features of claim 1~~ and an exhaust gas aftertreatment method ~~having the features of claim 11, both of which are described and claimed hereinafter.~~

- 5 The exhaust gas aftertreatment device according to the invention having a reforming unit for generating hydrogen by steam reforming, partial oxidation of hydrocarbons and/or mixed forms thereof is distinguished by the fact that the reforming unit is arranged directly in the main exhaust gas stream from an internal combustion engine. The
- 10 steam and residual oxygen which are required for the reforming preferably originate from the exhaust gas. The step of providing the required reducing agents consists in briefly switching the internal combustion engine, which is predominantly operated in lean-burn mode and the exhaust gas from which is undergoing the aftertreatment, to
- 15 rich-burn mode, allowing reforming by means of the reforming reactor according to the invention using the hydrocarbons which are present in the exhaust gas. Various specific measures for controlling the air/fuel ratio, also referred to as the air ratio λ for short, have already been proposed for this purpose, cf. for example laid-open specifications
- 20 EP 0 560 991 A1 and DE 196 26 835 A1.

In the reforming unit, an exothermic partial oxidation in the presence of residual oxygen or an endothermic steam reforming operation in the absence of oxygen takes place. The combination of the two processes,

which is characterized by an excellent heat balance, is referred to as autothermal reforming. Furthermore, the reforming reactor can also be operated as what is known as an autothermal reforming reactor, or ATR reactor for short.

- 5 During the reforming, the hydrocarbons in the exhaust gas are substantially converted into a CO- and H₂- containing gas mixture (synthesis gas). The reducing agents hydrogen (H₂), carbon monoxide (CO) and/or unburned hydrocarbons (HC) which are present here are subsequently used for the reduction of nitrogen oxides.
- 10 The apparatus according to the invention and the method according to the invention for exhaust gas aftertreatment, by virtue of the use of a reforming reactor or a reforming unit in the full flow of exhaust gas allow the synthesis gas yield in rich-burn mode to be optimized, which leads in an extremely advantageous way to an improvement to the NO_x
- 15 and sulfur regeneration of the NO_x storage catalytic converters and to a reduction in the HC emissions which occur. In addition, the NH₃ yield in rich-burn mode on the NO_x storage catalytic converter can be optimized.

- Cyclical rich-burn mode can be implemented either engine-internally
- 20 (e.g., afterinjection of fuel into the combustion chamber of the internal combustion engine or throttling), by a secondary injection into the exhaust gas stream upstream of the reforming reactor and/or by a

combination of the two options. NO_x which is produced in rich-burn mode is substantially broken down by reduction under the reforming conditions.

In lean-burn mode, the reforming reactor behaves like an oxidation
5 catalytic converter which is standard in the exhaust gas sector and reduces the gaseous emissions (HC , CO , NO_x) in the oxygen-rich exhaust gas. To allow a rapid cold start, the reforming unit may be equipped with a heating function, e.g., electrical, by means of a flame glow plug, etc.

10 In accordance with ~~claim 9~~ one aspect of the invention, an exhaust gas recirculation may optionally be provided downstream of the reforming unit. In rich-burn mode ($\lambda < 1$), therefore, it is possible to supply reformat to the engine combustion. This advantageously leads to a drop in the untreated emission levels and at the same time to a lower
15 fuel consumption.

In a refinement ~~as described in claim 2~~ of the invention, the at least one exhaust gas catalytic converter, which is preferably an NO_x storage catalytic converter which removes nitrogen oxides from lean exhaust gas by storing them as the exhaust gas flows through it and generates
20 N_2 by reducing the stored nitrogen oxides when reducing exhaust gas flows through it, is arranged in the main exhaust gas stream downstream of the reforming unit. In addition, NH_3 can be generated by

selecting suitable operating parameters. Furthermore, at least one further exhaust gas catalytic converter, which is preferably an SCR catalytic converter which reduces nitrogen oxides contained in the exhaust gas using NH_3 that has been generated by means of a nitrogen
5 oxide storage catalytic converter or stores excess NH_3 and then makes it available as reducing agent in lean-burn mode, is arranged downstream of the NO_x storage catalytic converter.

In a preferred configuration ~~as described in claim 3 of the invention~~, the at least one exhaust gas catalytic converter, which is preferably an SCR
10 catalytic converter which reduces nitrogen oxides contained in the exhaust gas using NH_3 that has been generated by means of the nitrogen oxide storage catalytic converter, is arranged in the main exhaust gas stream downstream of the reforming unit. Furthermore, at least one further exhaust gas catalytic converter, which is preferably an
15 NO_x storage catalytic converter which removes nitrogen oxides from lean exhaust gas by storing them as the exhaust gas flows through it and generates N_2 by reducing the stored nitrogen oxides when reducing exhaust gas flows through it, is arranged downstream of the SCR catalytic converter.

20 The use of nitrogen oxide storage catalytic converters, also known as NO_x storage catalytic converters or NO_x adsorber catalytic converters or NSC for short, is generally known for the post-engine lowering of the levels of nitrogen oxides in internal combustion engines operated in


lean-burn mode. Lean-burn operating phases of the internal combustion engine correspond to adsorption phases of the nitrogen oxide storage catalytic converter, in which it oxidizes nitrogen monoxide (NO) to form nitrogen dioxide (NO₂) and then stores the latter in the form of nitrates.

- 5 During brief, periodic regeneration or desorption phases, the stored nitrates are removed from the nitrogen oxide storage catalytic converter by being converted into nitrogen dioxide and then nitrogen monoxide. The latter is then reduced to nitrogen by suitable reducing agents.


- 10 A number of problem points are observed in this alternating adsorption/desorption operating sequence. For example, considerable quantities of the polluting gas ammonia (NH₃) may form in the regeneration phase as a result of hydrogen reacting with nitrogen monoxide and/or nitrogen dioxide, depending on the catalytic converter temperature, the exhaust gas composition and the material composition
- 15 of the nitrogen oxide storage catalytic converter. During the transition from a lean exhaust gas atmosphere to a rich exhaust gas atmosphere, there is a risk of undesirable breakthroughs of nitrogen oxides on account of sudden nitrate decomposition if a suitable quantity of reducing agent is not provided sufficiently quickly. During the
- 20 transition from a rich exhaust gas atmosphere to a lean exhaust gas atmosphere, the nitrogen oxide storage catalytic converter may be heated as a result of exothermic combustion reactions, with the result that nitrates which have already formed may decompose again and

temporarily can no longer be stored, which can cause undesirable nitrogen oxide slippage. With this NO_x storage catalytic converter technology, efficient lowering of the levels of nitrogen oxides is restricted to a relatively narrow temperature range approximately
5 between 200°C and 400°C, since at lower temperatures the oxidation of NO to NO₂ is inhibited and at higher temperatures the nitrates which have formed can no longer be stably stored in significant quantities and the thermodynamic equilibrium between NO and NO₂ increasingly shifts toward the side of the nitrogen monoxide. According to the
10 invention, the provision of synthesis gas expediently results in improved NO_x regeneration at a lower temperature, which in turn has an advantageous effect on the ageing properties and efficiency of the NO_x storage catalytic converter.

Typical NO_x storage catalytic converters contain alkaline-earth metals
15 and alkali metals, which are known for their nitrogen oxide storage capacity. Under lean conditions, the nitrogen oxides are converted as follows:



20 Under rich exhaust gas conditions, nitrogen dioxide is desorbed again from the store and directly reacted with the carbon monoxide present in the exhaust gas to form nitrogen oxide:



The switching times between lean and rich operating modes of the engine depend on the quantity of storage material used, the NO_x emissions and the parameters which are typical of all catalyzed reactions, such as gas throughput and temperature.

A further problem point when using sulfur-containing fuels is what is known as the sulfur poisoning of the NO_x storage catalytic converter caused by the accumulation of sulfates, which are more stable than the nitrates and do not decompose in the NO_x regeneration phases. Therefore, special desulfating phases at an increased exhaust gas temperature and a rich exhaust gas composition are usually carried out from time to time in order to remove the sulfates, cf. for example laid-open specification DE 198 27 195 A1. In this case too, in accordance with the invention, the provision of synthesis gas expediently results in improved sulfur regeneration or removal at the NO_x storage catalytic converter, likewise at a lower temperature, which in turn has an advantageous effect on the ageing properties of the NO_x storage catalytic converter. During desulfating, the polluting gas hydrogen sulfide (H₂S) may form; the emission of this gas should be avoided. For this purpose, for example in patent DE 100 25 044 C1, it is proposed that secondary air be fed into the exhaust section during the desulfating

phases in order to oxidize the hydrogen sulfide in a subsequent oxidation catalytic converter.

Functions which decide on the need for and possibility of deliberate generation of NH_3 and suitably predetermine the operating parameters, in particular the duration and extent of enrichment during the NSC regeneration, are preferably implemented in a corresponding control unit, which, by way of example, can also be used to control the combustion device, such as an internal combustion engine. The formation of NH_3 can typically be boosted by using a lower air ratio and a longer regeneration time, provided that the temperature of the NO_x storage catalytic converter is in the range in which the formation of NH_3 is possible. Furthermore, during NSC regeneration the operation of the combustion device can be set in such a way, in a manner which is known per se, that high untreated NO_x emission therefrom is achieved, and as a result the formation of NH_3 at the NO_x storage catalytic converter is further boosted.

By using a suitable arrangement of the components, it is possible to adapt the maximum thermal loading which occurs in the individual components to the specific requirements. Moreover, by suitable arrangement it can be ensured that the temperatures of the individual components in driving operation are in a range which is favorable for the particular function. The rich-burn mode which is required for regeneration of the NO_x storage catalytic converter can be realized by

engine-internal measures or an additional post-engine introduction of reducing agents (e.g., fuel into the exhaust section upstream of the reformer), referred to below as secondary injection.

The post-engine supply of reducing agent upstream of the NO_x storage catalytic converter can also be used to set rich conditions for NSC regeneration when the engine is operating with a lean exhaust gas. This preferably takes place when the engine is operating at between $\lambda = 1.0$ and $\lambda = 1.2$, since otherwise the quantity of reducing agent which needs to be supplied is too great. This has the advantage that a high untreated emission of NO_x usually occurs in the range between $\lambda = 1.0$ and $\lambda = 1.2$, whereas these emissions are significantly lower at air ratios $\lambda < 1$. Consequently, this method can be used to achieve a high NO_x emission and therefore extensive formation of NH₃ during the NSC regeneration.

To avoid high CO and HC emissions during NSC regenerations with $\lambda < 1$, if necessary secondary air can be blown in upstream of a subsequent oxidation catalytic converter. The secondary air may be provided, for example, by an electrically driven secondary air pump or a compressor or may be removed downstream of the compressor in the case of supercharged engines.

Another known exhaust gas aftertreatment method is what is known as the selective catalytic reduction method, also referred to as the SCR

method for short. In this case, to reduce nitrogen oxides, a reducing agent with a selective action, typically ammonia, is added to the exhaust gas. The ammonia is temporarily stored in a corresponding nitrogen removal catalytic converter, referred to as SCR catalytic converter for short, and used by the latter to catalytically reduce nitrogen oxides (NO_x) contained in the exhaust gas to form nitrogen and water. At low temperatures, the efficiency of SCR catalytic converters is highly dependent on the NO/NO_2 ratio, with a maximum efficiency at an NO_2 content of approx. 50% for temperatures below 200°C and a significantly reduced efficiency if the NO_2 content is lower. At higher temperatures above approx. 400°C , the nitrogen oxide reduction is limited by oxidation of ammonia, and moreover the ammonia storage capacity of the SCR catalytic converter decreases as the temperature rises. The overall result for SCR systems of this type is a useful temperature window for efficient lowering of the levels of nitrogen oxides of approximately 250°C to approximately 550°C . SCR catalytic converters are subject to thermal ageing and should not be exposed to temperatures of over approx. 700°C to 750°C . The lean-burn phases can be extended by the NH_3 stored in the SCR catalytic converter, which advantageously brings about fuel savings and at the same time improved ageing properties of the NSC catalytic converter. It has been found that the SCR catalytic converter can also be used to avoid H_2S emission, which occurs, for example, during desulfating. Tests have

shown that an SCR catalytic converter, on account of its specific properties, can oxidize hydrogen sulfide which is produced during desulfating to SO_2 even with a rich exhaust gas composition ($\lambda < 1$). This makes it possible to avoid unpleasant odor pollution.

5 As a further particular feature, SCR catalytic converters can temporarily store hydrocarbons (HC) which are unburned at low temperatures and, if they contain vanadium pentoxide (V_2O_5), can also oxidize the hydrocarbons under rich conditions ($\lambda < 1$). It is as a result usually possible to reduce the breakthrough of reducing agent during
10 the NSC regeneration, and also, on account of its property of storing hydrocarbons at low temperatures, to contribute to lowering the HC emission levels after a cold start. In particular the emissions of possibly carcinogenic hydrocarbons, such as benzene, toluene, ethylbenzene and xylene, which may form during rich conditions at the NO_x storage
15 catalytic converter, can be lowered. The HC stored at low temperatures are released again at higher temperatures and can be oxidized at the SCR catalytic converter or a downstream oxidization catalytic converter. However, the high temperatures which are required for the oxidization of unburned hydrocarbons at the SCR catalytic converter
20 lead to a deterioration in the ageing properties. This can be overcome by the invention, since the use of the reformer unit in the full flow, with the reformer unit simultaneously functioning as a reformer or reformat-generating unit, allows the synthesis gas content in rich-burn

mode to be increased, while at the same time lowering the levels of HC emissions. As a further benefit, this leads to improved ageing properties in the SCR catalytic converter.

Typical SCR catalytic converters contain V_2O_5 , TiO_2 and at least one of the components selected from the group consisting of tungsten oxide, molybdenum oxide, silicon dioxide and zeolites.

In a further advantageous embodiment ~~as described in claim 10 of the invention~~ for post-engine lowering of the levels of particulates, the reforming unit is designed as a catalytic particulate filter. This catalytically active diesel particulate filter is designed as a wall-flow filter. The reforming unit therefore extremely advantageously serves simultaneously as a reformer and as a particulate filter. In addition to the fact that it can be arranged in the full flow of exhaust gas, obviating the need for an additional filter unit, this also leads to a significantly more compact overall design. Moreover, combining or integrating two of the abovementioned functions in one component allows the space required to be considerably reduced.

This particulate filter retains the particulates which are emitted with a high degree of efficiency. The filter can be regenerated by various measures. Since particulates burn off at elevated temperatures, on the one hand the filter temperatures or the exhaust gas temperatures can be increased (e.g., by afterinjection of fuel into the exhaust section), or

on the other hand the particulate ignition temperatures can be lowered by catalytic coating or by adding additives to the fuel, to ranges of < 400°C, in which case the reduction of the ignition temperature leads to the required afterinjection time being shortened or to a reduction in
5 the afterinjection quantity. A combination of various regeneration methods is also possible. In general, coated particulate filters are far superior to adding additives to the fuel with regard to emissions during the regeneration phase. When the layer of particulates is burnt off, which requires exhaust gas temperatures of over 550°C, CO₂ and steam
10 are formed from the particulates. If the exhaust gas which reaches the particulate filter contains NO₂, oxidation of particulates by reaction with NO₂ is also already taking place in the temperature range from approximately 250°C to 400°C (CRT effect).

The reforming unit which simultaneously functions as a particulate
15 filter contains, as support material for an exhaust gas catalytic converter, a ceramic monolith, for example of cordierite, a ceramic with the empirical formula $2\text{MgO} \times 2\text{Al}_2\text{O}_3 \times 5\text{SiO}_2$, silicon carbide (SiC) or other suitable materials. The catalytic coating mainly contains support oxides, further oxidic components, such as for example cerium oxide,
20 and precious metals, which are applied to the ceramic monolith as an aqueous coating, also known as washcoat. The support oxides used may, for example, be Al₂O₃, SiO₂, TiO₂, zeolites or mixtures thereof, and elements from the rare earths or Zr, optionally in the form of oxides,

may also be present in order to increase the specific surface area. In practice, in particular the precious metals have proven to be effective catalysts, in particular Pt, Rh, Pd, Ir, Ru and Ni.

The heating of the NO_x storage catalytic converter for desulfating and of
5 the particulate filter for thermal regeneration can be effected by engine-internal measures, including afterinjection of fuel into the combustion chamber. The regeneration of the NO_x storage catalytic converter is carried out by means of the H₂ and CO formed in the reformer. In addition to the deliberately higher exhaust gas
10 temperature, incompletely burnt hydrocarbons which remain in the exhaust gas lead to additional exothermicity on a catalytic converter which is optionally arranged close to the engine, thereby further raising the exhaust gas temperature. In addition or as an alternative, it is also possible for reducing agents (e.g., fuel) to be supplied in the exhaust
15 section immediately upstream of the component(s) to be heated and/or upstream of an oxidization catalytic converter which precedes these components. This has the advantage that the heat losses caused by having to heat further upstream components and heat losses caused by cooling in the exhaust pipe are reduced. As a result, the energy
20 consumption and therefore the increased fuel consumption for heating are reduced to a minimum. A further advantage is that in this way further upstream components are not exposed to high exhaust gas temperatures, and consequently their thermal ageing can be restricted

to a minimum. Moreover, this prevents further upstream components, e.g., an upstream NO_x storage catalytic converter, from leaving the temperature window which is required for a good efficiency as a result of being heated.

5 In the case of a catalytically coated particulate filter, a further advantage is that the conversion of fuel continues to be possible even, for example, after prolonged overrun phases of the internal combustion engine with a low exhaust gas temperature, on account of the high heat capacity of the particulate filter. By contrast, with a conventional
10 catalytic converter, there is a risk of the temperature under similar conditions dropping below the light-off temperature on account of the low heat capacity, so that catalytic conversion of the hydrocarbons is no longer possible. In general, instead of supplying reducing agent (e.g., fuel) upstream of a catalytic converter, it is also possible to use other
15 heating methods instead of supplying reducing agents downstream of the engine. Examples which may be mentioned include electrical heating of the particulate filter/reformer, as measures which are used as standard in practice.

In a particular feature ~~as described in claim 4 of the invention~~, the at
20 least one exhaust gas catalytic converter is arranged in the main exhaust gas stream downstream of the reformer reactor, the exhaust gas catalytic converter having the functions of an NO_x storage catalytic converter and an SCR catalytic converter. Combining or integrating the

two functionalities in one component again allows the space taken up to be considerably reduced.

In a preferred refinement ~~as described in claim 5~~ of the invention, an oxidation catalytic converter is arranged downstream of in each case
5 the last exhaust gas catalytic converter.

In a further configuration ~~as described in claim 6~~ of the invention, a three-way catalytic converter is arranged immediately after the reforming unit, as seen in the main direction of flow of the exhaust gas.

In another advantageous refinement of the invention ~~as described in~~
10 ~~claim 7~~, the at least one exhaust gas catalytic converter, which is preferably a DENOX catalytic converter, is arranged in the main exhaust gas stream downstream of the reforming unit. The DENOX catalytic converter may, for example, contain zeolite, Al_2O_3 and/or perovskite as support material, and for example Pt, Cu or other suitable
15 metals as catalytically active components.

According to a further advantageous design ~~as described in claim 8~~ of the invention, an NO_x storage catalytic converter is arranged upstream or downstream of the DENOX catalytic converter.

The method for operating an exhaust gas aftertreatment device ~~as~~
20 ~~described in claim 11~~ of the invention allows reduction of nitrogen oxides in exhaust gases from motor vehicles by reduction at a catalytic

converter in which hydrogen is supplied, the hydrogen which is required for the nitrogen oxide reduction being generated onboard the motor vehicle by steam reforming, partial oxidation of hydrocarbons and/or mixed forms thereof. In this case, according to the invention, the reforming is carried out directly in the main exhaust gas stream from an internal combustion engine. The steam and residual oxygen required for the reforming preferably originate from the exhaust gas.

In a preferred configuration of the method ~~as described in claim 12~~, the temperature of the reforming unit is set by means of the air/fuel ratio, with the current oxygen concentration in the exhaust gas being determined with the aid of a wide-band lambda sensor.

~~In a method as described in claim 13~~, in accordance with the invention the reforming unit is operated at an air/fuel ratio in the range from approximately $0.5 < \lambda < 1.0$.

Furthermore, in accordance with a refinement of the method ~~as described in claim 14~~, a quantity of fuel which is fed to the reforming reactor is set engine-internally, by means of a secondary injection and/or by a combination of the two options.

It will be understood that the features described above and those which are yet to be explained below can be used not only in the combination given in each instance but also in other combinations or as stand-alone features without departing from the scope of the present invention.

Further advantages and configurations of the invention will emerge from the claims and the description. In particular, advantages result from a suitable combination or integration of various catalytic converter components as explained below.

- 5 The invention is explained in more detail below with reference to the drawing, ~~in which, by way of example and in diagrammatic form,~~

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows a block diagram illustration of an exhaust gas
10 aftertreatment apparatus in the full exhaust gas flow, which includes, in series, a reforming/particulate filter unit, an NO_x storage catalytic converter and an SCR catalytic converter,

Fig. 2 shows a block diagram illustration of an exhaust gas
aftertreatment apparatus in the full flow of exhaust gas, which
15 includes, in series, a reforming/particulate filter unit and an integrated exhaust gas catalytic converter with an NO_x storage and SCR catalytic converter function,

Fig. 3 shows a block diagram illustration of an exhaust gas
aftertreatment apparatus in the full flow of exhaust gas, which
20 includes, in series, a reforming/particulate filter unit, a three-way catalytic converter, an NO_x storage catalytic converter and an SCR

catalytic converter, and

Fig. 4 shows a block diagram illustration of an exhaust gas aftertreatment apparatus in the full flow of exhaust gas, which includes, in series, a reforming/particulate filter unit and an
5 HC-DENO_x storage catalytic converter.

DETAILED DESCRIPTION OF THE DRAWINGS

The exhaust gas aftertreatment device shown in Fig. 1 includes, as seen in the direction of flow of exhaust gas, downstream of an internal combustion engine (not shown), a reforming unit 1, which
10 simultaneously acts as a particulate filter, an NO_x storage catalytic converter 2 and an SCR catalytic converter 3 as components which purify the exhaust gas arranged in succession in the full flow of the exhaust section 4. A control unit (not shown in more detail) is used to control the internal combustion engine, which is preferably a diesel
15 engine, and the exhaust gas aftertreatment device. Furthermore, not illustrated in more detail, temperature sensors, NO_x sensors, lambda sensors, a device for supplying secondary air and pressure sensors may be arranged at suitable positions in the exhaust section 4. A device for supplying reducing agent 5 after the engine, also referred to as
20 secondary injection, is arranged upstream of the reforming unit 1.

The internal combustion engine delivers exhaust gas which contains, inter alia, NO_x, particulates, CO and HC as unburned hydrocarbons. In lean-burn mode ($\lambda > 1$), the reforming unit 1 behaves as a normal oxidation catalytic converter and CO and HC are oxidized to CO₂ and H₂O. The particulates which are present in the exhaust gas are retained in the reforming unit 1, which simultaneously acts as a particulate filter. Some of the particulates which have accumulated in the particulate filter are oxidized by reaction with NO₂, reducing NO₂ to NO. If the exhaust gas downstream of the NO_x storage catalytic converter 2 still contains nitrogen oxides, these nitrogen oxides are mostly in the form of NO. In lean-burn mode, NO_x is stored in nitrate form in the NO_x storage catalytic converter 2. In rich-burn mode ($\lambda < 1$), the reforming unit 1 delivers a CO- and H₂- containing synthesis gas mixture with a reduced HC content. Then, in rich-burn mode, accumulated NO_x is desorbed and reduced using synthesis gas or CO and/or HC to form N₂. In addition, ammonia is also formed, in accordance with the equation $3.5\text{H}_2 + \text{NO}_2 \rightarrow \text{NH}_3 + 2\text{H}_2\text{O}$. This NH₃ can directly reduce the NO_x formed in rich-burn mode at the subsequent SCR stage 3 in accordance with the equation $4\text{NH}_3 + 3\text{NO}_2 \rightarrow 3.5\text{N}_2 + 6\text{H}_2\text{O}$. Excess ammonia is stored by adsorption in the SCR catalytic converter 3. This allows NO_x which is present already to be partially converted in lean-burn mode. This allows the lean-burn phases to be lengthened, with the advantage of fuel saving

and improvement to the ageing properties of the NO_x storage catalytic converter 2. An exhaust gas recirculation (not shown) may optionally be provided downstream of the reforming unit and upstream of the NO_x storage catalytic converter 2. Consequently, in rich-burn mode, reformate can be fed to the engine combustion. This leads to a drop in the level of untreated emissions and at the same time reduces the fuel consumption. In rich-burn mode, the temperature of the reforming unit 1 is controlled by varying lambda. For a fast cold-start, the reforming unit can be provided with a heating function (e.g., electrical, flame glow plug, etc.).

It is optionally also possible to swap over the order of NO_x storage catalytic converter 2 and an SCR catalytic converter 3 as components which purify the exhaust gas, with the result that the reduction of NO_x at the SCR catalytic converter 3 takes place using H₂ or reformate instead of using NH₃.

An oxidization catalytic converter with an oxygen storage function connected downstream of both versions converts the hydrocarbons which still remain as the engine is switched from lean-burn to rich-burn mode, by means of stored O₂. A device for supplying secondary air (not

shown) may also be connected upstream of the oxidation catalytic converter.

Heating measures can be applied to achieve temperatures which are
5 sufficient at the components which purify exhaust gas, in particular at
the NO_x storage catalytic converter 2 and at the SCR catalytic converter
3, even during low-load operation, and thereby to achieve optimum
reduction in the levels of NO_x. These heating measures may be
engine-internal, e.g., a late shift in the main injection or afterinjection
10 into the combustion chamber, or also post-engine, by supplying
reducing agent upstream of the reforming unit 2 in order to generate
exothermicity, provided that the NO_x storage catalytic converter 2 has
reached a sufficient temperature to convert the reducing agent.
Furthermore, the exhaust pipe may be thermally insulated in order to
15 minimize heat losses from the exhaust gas. By way of example, it is
possible to use an air gap insulation. Further measures used to increase
the exhaust gas temperature may include: increasing the idling speed,
lengthening the afterglow time, connecting up additional electrical
consumers or increasing the EGR rate. The abovementioned measures
20 can be controlled, for example, by a control unit for controlling the
engine and/or exhaust-gas purification components as a function of the
input temperature signals or by means of a model. By way of example,
models for the untreated NO_x emission, the NO_x storage properties of

the NO_x storage catalytic converter 2, the NH₃ formation at the NO_x storage catalytic converter 2 and the NH₃ storage in the SCR catalytic converter 3, which define, inter alia, the criteria for an NSC regeneration, are stored in the control unit. The models can be adapted
5 to the current ageing state of the catalytic converters on the basis of various sensor signals.

Thermal regenerations of the reforming unit 1, which also acts as a particulate filter, are required at regular intervals, so that the flow resistance is not increased by the particulate deposits, which would
10 reduce the engine power. The layer of particulates is burnt off, with CO₂ and steam being formed from the particulates. The combustion of particulates normally requires temperatures of over 550°C. However, with a catalytic particulate filter, it is possible to lower the particulate ignition temperature into the range below 400°C. The reaction takes
15 place in a similar way to in a CRT system, i.e. NO is converted into NO₂ which reacts with the particulates. By way of example, a supply of reducing agent downstream of the engine can be used to heat the particulate filter 1.

20 The exemplary embodiment illustrated in Fig. 2 differs from that shown in Fig. 1 by virtue of the fact that the exhaust gas purification components NO_x storage component 2 and the one SCR catalytic

converter 3 arranged downstream in the full flow of the exhaust gas are combined to form an integrated exhaust gas catalytic converter 6. This has the advantage that an integrated solution avoids the temperature drop in the exhaust pipe which occurs in the case of catalytic converters connected in series. An advantage in this case is that this measure considerably reduces the space taken up. Moreover, both functional components reach the required operating temperature very quickly after a cold start, so that there is no need for any additional heating measures, which would increase the fuel consumption. In the integrated nitrogen oxide storage and SCR catalytic converter, a significant proportion of the nitrogen oxides contained in the exhaust gas is temporarily stored, while the remainder is reduced by ammonia which has been temporarily stored therein. In this case too, an oxidation catalytic converter with an oxygen storage function can be connected downstream of a device for supplying secondary air connected upstream of this catalytic converter.

The exhaust gas catalytic converter which is in integrated form may generally be in the form of a honeycomb body designed as an unsupported extrudate; this means that the components of the catalytic converter are processed to form an extrudable compound and then extruded to form honeycomb bodies. A catalytic converter of this type consists of catalyst material all the way through and is therefore also

referred to as a full catalyst. In the present case, SCR catalyst component 3 can be extruded to form a honeycomb body, and the NO_x storage catalyst component 2 can be applied to the walls of the flow passages in the form of a coating. The person skilled in the art will be aware of the techniques used for this purpose. However, the NO_x storage catalytic converter 2 and the SCR catalytic converter 3 may also be applied in the form of a coating to the walls of the flow passages of catalytically inert support bodies in honeycomb form. The inert support bodies preferably consist of cordierite. In a further embodiment of the catalytic converter, the NO_x storage catalyst component 2 and the SCR catalyst component 3 are applied to the inert support body in two separate layers, with the NO_x storage catalyst component 2 preferably being arranged in the lower layer which bears directly against the support body, and the SCR catalyst component 3 preferably being arranged in the upper layer, which comes into direct contact with the exhaust gas.

The exhaust gas aftertreatment device which has already been described in Fig. 1, with a reforming unit 1 which simultaneously acts as a particulate filter, an NO_x storage catalytic converter 2 and an SCR catalytic converter 3 as components which purify the exhaust gas, as a further embodiment in the example shown in Fig. 3, also has a three-way catalytic converter (TWC) 7 connected directly upstream of

the NSC catalytic converter 2. This functions firstly as an additional
NH₃ generator, by using the H₂ or reformat delivered by the reforming
unit 1 to contribute to the reduction of nitrogen oxides, and secondly, on
account of its oxygen storage function, it is able to partially oxidize
5 unburned hydrocarbons, so that it contributes to significantly
increasing the efficiency of the SCR catalytic converter 3. In this
exemplary embodiment too, the SCR catalytic converter 3 may be
connected upstream of the NO_x storage catalytic converter 2, so that the
TWC catalytic converter 7 is connected upstream of the SCR catalytic
10 converter. In a further variant, the two components SCR catalytic
converter 3 and NO_x storage catalytic converter may be designed as an
integrated exhaust gas catalytic converter 7, upstream of which the
TWC catalytic converter 7 is connected.

15 Fig. 4 shows a further variant of an exhaust gas aftertreatment device,
in which an HC-DENOX catalytic converter 8 is arranged downstream
of the reforming unit 1, in the full flow of the exhaust section. It
replaces the "NSC catalytic converter with downstream SCR catalytic
converter" variant, catalysing the nitrogen oxide reduction by means of
20 HC. In order also to maximize the conversion of nitrogen oxides, it is
possible for an NO_x storage catalytic converter 2 to be arranged
immediately upstream or downstream of the HC-DENOX catalytic
converter.